

# Commercial 95<sup>®</sup>



Product Profile

Shadecloth Range

Rev.13 5/13

## Product Description

Commercial 95<sup>®</sup> is a high quality knitted shade fabric supplied in bulk rolls, designed for tension structures, awnings and shade covers specifically for commercial architectural applications.

## Material

Yarn UV stabilised HDPE  
Construction Monofilament & tape  
Pattern Lock-stitch knitted  
Temperature range -30°C to +75°C

## Features

- Strong HDPE 100% recyclable fabric won't rot or absorb moisture.
- Stentered (heat-set) to reduce shrinkage and for ease of fabrication.
- 10 year UV degradation warranty on fabric.
- 100% Lead and Phthalate free
- Greenguard<sup>®</sup> and Oeko-Tex<sup>®</sup> certified
- Engineered in Australia to meet the harsh

## Usage Instructions

- Do not use against flames.
- Contact with organic solvents, halogens or highly acidic substances may reduce the service life of the fabric and void the warranty.
- Biaxial elastic material properties available on request.

## Properties

Nominal fabric mass 340 gsm ± 20  
(AS 2001.2.13)

Approximate thickness 1.6 mm

## Performance

Tensile Strength - Warp 635 N/50mm  
Elongation at break 95.6 %

Tensile Strength - Weft 2494 N/50mm  
Elongation at break 70.4 %

(AS 2001.2.3.1)

Wing Tear – Warp (mean) 187 N

Wing Tear – Weft (mean) 359 N

(AS 2001.2.10)

Bursting Pressure (mean) 3500 kPa

(AS 2001.2.4)

Bursting Force (mean) 2146 N

(AS 2001.2.19)

## Flammability

(AS 1530.2)

Flammability Index (range 0-100) 14

## Suggested Specification

Shadecloth fabric shall be compliant to Australian standard AS 4174 and shall be Synthesis Commercial 95 knitted HDPE monofilament & tape shade fabric offering a UV block up to 97%.

Colour	Code	Nom Width	Length	Cover Factor	Shade Factor	Av % Trans	Av. UVR Trans	Av. PAR Trans	% UVR Block	UPF Rating	UPF Mean
Aquatic Blue	444938	3.00 m (folded)	40 m	96.8%	90.2	9.8%	6.4%	11.2%	93.6%	15.0	32.2
Black	444945			98.2%	97.4	2.6%	2.7%	97.4%	35.0	59.8	
Brunswick Green	444952			96.2%	93.9	6.1%	4.9%	6.3%	95.1%	15.0	32.6
Cayenne	455255			92.0%	87.0	13.0%	6.0%	11.6%	94.0%	11.0	14.7
Cedar	465360			94.9%	87.7	12.3%	5.3%	12.6%	94.7%	18.0	19.4
Charcoal	444969			94.7%	94.2	5.8%	5.3%	5.8%	94.7%	11.4	23.2
Cherry Red	444976			90.1%	75.3	24.7%	10.7%	22.4%	89.3%	8.8	12.1
Desert Sand	444983			94.0%	85.0	15.0%	3.6%	16.1%	96.4%	10.0	20.3
Deep Ochre	444990			95.1%	91.3	8.7%	5.6%	8.5%	94.4%	12.1	26.3
Gun Metal	455262			97.1%	96.2	3.8%	2.3%	3.9%	97.7%	23.0	54.9
Natural	445003			97.9%	74.3	25.7%	3.2%	30.1%	96.8%	35.0	62.4
Navy Blue	445010			96.2%	94.4	5.6%	4.8%	5.7%	95.2%	14.7	33.3
Rivergum Green	445027			94.7%	85.0	15.0%	7.7%	15.6%	92.3%	12.6	20.8
Sky Blue	445034			95.2%	90.4	9.6%	6.2%	9.9%	93.8%	16.0	21.3
Steel Grey	445041			95.6%	88.4	11.6%	7.0%	12.3%	93.0%	13.1	26.1
Turquoise	445058			94.0%	90.0	10.0%	5.7%	11.7%	94.3%	11.9	18.0
Yellow	445072			98.3%	77.2	22.8%	2.9%	25.0%	97.1%	45.0	71.3

Approx. roll weight: 44 kg  
Approx. roll diameter: 0.32 m  
Core diameter: 35 mm

Tested according to AS 4174 Synthetic Shadecloth

Av. % Transmis. = Average % Transmission within the 290-770nm spectrum

Av. UVR Transmis. = Average % Transmission within the 290-400nm spectrum

Av. PAR Transmis. = Average % Transmission within the 408-770nm spectrum

UPF (Ultraviolet Protection Factor)

UPF (Rating) = actual rating assigned to material tested, inc standard deviation.

UPF (Mean) = average of UPF values tested, excludes standard deviation.

The above results are typical averages from independent testing and quality assurance testing and are not to be taken as a minimum specification nor as forming any contract between Gale Pacific and another party. Due to continuous product improvement, Product Profiles are subject to alteration without notice.

Notice: As the use and disposal of this product are beyond Gale Pacific's control, regardless of any assistance provided without charge, Gale Pacific assumes no obligation or liability for the suitability of its products in any specific end use application. It is the customer's responsibility to determine whether Gale Pacific's products are appropriate for the specific application and complies with any legal & patent regulations.

## FOR MORE INFORMATION – PLEASE CONTACT:

Australia	Gale Pacific Ltd. PO Box 892, Braeside, Victoria, 3195	Phone +61 3 9518 3399	Fax +61 3 9518 3398
NZ	Gale Pacific (NZ) Ltd. PO Box 65 527, Mairangi Bay, Auckland	Phone +64 3 373 9500	Fax +64 3 373 9501
UAE	Gale Pacific FZE. PO Box 17696, Jebel Ali, Dubai	Phone +971 4 881 7114	Fax +971 4 881 7167
USA	Gale Pacific Inc. Suite 1704, 285 W. Central Parkway, Altamonte Springs, Florida, 32714	Phone +1 407 772 7979	Fax +1 407 772 0553